

Magic angle effects of the one-dimensional axis conductivity in quasi-one dimensional conductors

Yasumasa Hasegawa¹, Hirono Kaneyasu¹, and Keita Kishigi²

¹*Department of Material Science,
Graduate School of Material Science,
University of Hyogo
Ako, Hyogo 678-1297, Japan*

²*Faculty of Education, Kumamoto University,
Kurokami 2-40-1, Kumamoto, 860-8555, Japan
(Dated: February 2, 2008)*

In quasi-one-dimensional conductors, the conductivity in both one-dimensional axis and interchain direction shows peaks when magnetic field is tilted at the magic angles in the plane perpendicular to the conducting chain. Although there are several theoretical studies to explain the magic angle effect, no satisfactory explanation, especially for the one-dimensional conductivity, has been obtained. We present a new theory of the magic angle effect in the one-dimensional conductivity by taking account of the momentum-dependence of the Fermi velocity, which should be large in the systems close to a spin density wave instability. The magic angle effect is explained in the semiclassical equations of motion, but neither the large corrugation of the Fermi surface due to long-range hoppings nor hot spots, where the relaxation time is small, on the Fermi surface are required.

PACS numbers: 74.70.Kn, 75.30.Fv, 75.47.-m

Quasi-one-dimensional organic conductors show a lot of interesting phenomena, such as unconventional superconductivity, spin density wave (SDW), field-induced spin density wave, quantum Hall effect, etc[1]. By studying the interaction of electrons with impurities as well as interaction between electrons Lebed and Bak[2] have predicted that the resistance, R_{xx} , has peaks at the magic angles $\theta = \tan^{-1}(\frac{b}{c}\frac{p}{q})$, where p and q are mutually prime integers and b and c are lattice constants, when the magnetic field is rotated in the plane perpendicular to the most conducting a axis. Experimentally, dips, instead of peaks, of the resistance at the magic angles are observed in both R_{xx} and R_{zz} in various quasi-one-dimensional organic conductors, (TMTSF)₂ClO₄[3, 4], (TMTSF)₂PF₆[5, 6], (TMTSF)₂ReO₄[7], (DMET)₂I₃[8], (DMET)₂CuCl₂[9], (DMET-TSeF)₂AuCl₂[10] and (DMET-TSeF)₂AuI₂[10, 11]. It is called as the magic angle effect(MAE).

Other angle dependences of the magnoresistance have also been observed in quasi-two-dimensional conductors[12, 13, 14], and in quasi-one-dimensional conductors with rotating magnetic field in the a - c plane[15] and in the a - b plane[16]. These angle dependences are explained in the semiclassical theory[15, 16, 17, 18] and they are used as powerful tools to observe the shape of the Fermi surface in low-dimensional systems.

For MAE, however, no complete explanation has been given yet, although there exist several theories[19, 20, 21, 22, 23, 24, 25, 26, 27, 28]. Interesting idea of the magnetic-field-induced confinement[22] has been proposed to explain MAE. Difference between the ground states at the magic angles and at other directions of the magnetic field is observed by the metallic and non-metallic temperature dependence of the resistance[6]. In

recent NMR experiment[29], however, no evidence for the change of the excitation spectrum at the magic angles has been obtained. This fact suggests that semiclassical approach, or equivalently Green function approach using the linearized k_x dispersion, can be applied in these systems. Indeed, MAE can be explained qualitatively in the semiclassical theory. By using the semiclassical equations of motion for the noninteracting electrons in the tilted magnetic field, Osada et al.[19] have shown that the conductivity in the z axis σ_{zz} shows peaks at the magic angles. In quasi-one-dimensional conductors the energy dispersion is described as $\epsilon_{\mathbf{k}} = -2t_a \cos ak_x - 2t_b \cos bk_y - 2t_c \cos ck_z - \mu$. Here we take the simple cubic lattice with lattice constant a , b , and c for simplicity. Since $t_a \gg t_b > t_c$, the Fermi surface is two nearly parallel sheets at $k_x \approx \pm k_F$ and $k_F = \frac{\pi}{4a}$ for the quarter-filled band. Osada et al[19] used the linearized dispersion in the k_x direction as

$$\epsilon_L(\mathbf{k}) = \pm \hbar v_F(|k_x| - k_F) - \sum_{m,n} t_{mn} \cos(mbk_y + nck_z), \quad (1)$$

and constant relaxation time τ . They have shown that peaks appear in σ_{yy} and σ_{zz} at the magic angles and the heights of peaks are proportional to t_{pq}^2 . In order to explain the experimental results of the perpendicular magnetoresistance, unphysically large values of t_{pq} are required. This model also fails to explain the magnitude of the recently observed giant Nernst effect[30] at the magic angles. Maki[21] has used the similar approximation of the linearized dispersion and constant τ , but took account of the k_y dependence of v_x in perturbation in $\frac{t_b}{t_a}$. Recently, Lebed et al.[26, 27] have emphasized the importance of the k_y dependence of v_x , or the density of states on the Fermi surface. They show that there occurs the

1D to 2D dimensional crossover when the magnetic field is at magic angles. In these approximation resonance-like peaks in σ_{zz} at the magic angle with $q = 1$ is obtained, but its height is proportional to $(\frac{t_b}{t_a})^{2p}$ and very small in the case of $t_b \ll t_a$ [21].

The more serious discrepancy between the semiclassical theories of MAE and experiments is encountered in the one-dimensional conductivity σ_{xx} . In the model of Osada et al.[19], σ_{xx} does not depend on the direction of the magnetic field. Maki[21] has pointed out that σ_{xx} shows peaks at magic angles, if the k_y and k_z dependence of v_x is taken into account. It is, however, very weak, i.e., it is of the order of $(\frac{t_b}{t_a})^2$. Meanwhile, Chaikin[20] has shown that the angular-dependence of σ_{xx} can be explained, if there are *hot spots* on the Fermi surface, where τ is small.

In this letter we show that the peaks in one-dimensional conductivity σ_{xx} at the magic angles are dramatically enhanced, when v_x depends strongly on k_y and k_z on the Fermi surface, even when long-range hopping terms and hot spots are absent. In quasi-one dimensional organic conductors, electrons correlate strongly and the system is close to the insulating state of SDW or field-induced SDW due to the nearly perfect nested Fermi surface. Then v_x on the Fermi surface depends on k_y and k_z much stronger than in perturbation in $\frac{t_b}{t_a}$ and $\frac{t_c}{t_a}$ studied by Maki[21] and Lebed et al.[25, 26]. The effect of electron correlation on v_x and τ can be calculated by using the random phase approximation for the quasi-one dimensional Hubbard model, which we will show in another publication[31]. In order to show MAE due to the k_y and k_z dependence of v_x , we calculate σ_{xx} in the model that the velocity v_x in some region on the Fermi surface differs sufficiently from that in the other region.

We assume the constant τ . Then the conductivity is calculated as[16, 19, 23, 24]

$$\sigma_{ij} = \frac{2e^2}{V} \sum_{\mathbf{k}} \left(-\frac{df}{d\epsilon_{\mathbf{k}}} \right) v_i(\mathbf{k}(0)) \int_{-\infty}^0 v_j(\mathbf{k}(t)) e^{\frac{t}{\tau}} dt \quad (2)$$

where i and j are x , y or z , and $v_i(\mathbf{k}(t))$ is the velocity on the Fermi surface in the semiclassical picture

$$\mathbf{v}(\mathbf{k}(t)) = \frac{1}{\hbar} \frac{\partial E(\mathbf{k})}{\partial \mathbf{k}(t)}. \quad (3)$$

The velocity $\mathbf{v}(\mathbf{k}(t))$ depends on time via the time dependence of the wave vector $\mathbf{k}(t)$ as

$$\hbar \frac{d\mathbf{k}(t)}{dt} = -e\mathbf{v}(\mathbf{k}(t)) \times \mathbf{B} \quad (4)$$

where we take the magnetic field $\mathbf{B}$ in the $y-z$ plane, $B_x = 0$, $B_y = B \sin \theta$, and $B_z = B \cos \theta$.

When $\theta = \tan^{-1}(\frac{b}{c} \frac{p}{q})$, $\mathbf{k}$ started from some point $\mathbf{k}(0)$ moves in the commensurate trail on the Fermi surface before coming back to $\mathbf{k}(0)$, while it travels all the Fermi




FIG. 1: (a) Simple model that v_x is αv_0 in the small rectangular region and v_0 in the other region in the Brillouin zone. (b) Extended Brillouin zone for $\tan \theta = \frac{p}{q} = \frac{2}{3}$. The gray region should be translated to the first Brillouin zone.

surface when $\frac{c}{b} \tan \theta$ is an irrational number. This is the main idea of the Chaikin's hot spots and other semiclassical theories of MAE. In order to simplify the calculation, we assume $v_x = v_0$ except for in the rectangular region of $2\pi\delta \times 2\pi\delta w$, where $v_x = \alpha v_0$ ($\alpha \neq 1$), as shown in Fig. 1(a) and $a = b = c = 1$. In the quasi-one dimensional system the density of states on the Fermi surface can be expressed as a function of energy ϵ , k_y and k_z as

$$N(\epsilon, k_y, k_z) = \frac{1}{|\hbar v_x(\epsilon, k_y, k_z)|} \quad (5)$$

At low temperature we can replace $-\frac{\partial f}{\partial \epsilon_{\mathbf{k}}}$ by $\delta(\epsilon - \epsilon_F(k_y, k_z))$ in Eq.(2) and we obtain

$$\sigma_{xx} = 2 \frac{2e^2}{\hbar V} \sum_{k_y, k_z} \int_{-\infty}^0 v_x(\mathbf{k}(t)) e^{\frac{t}{\tau}} dt, \quad (6)$$

where summation on k_y and k_z should be done on the right sheet of the Fermi surface ($v_x(\mathbf{k}(t)) > 0$). A factor of 2 comes from the contribution of the left sheet of the Fermi surface. Although σ_{zz} is given by the correlation of $v_z(\mathbf{k}(0))$ and $v_z(\mathbf{k}(t))$ in Eq.(2), σ_{xx} in quasi-one dimensional system is simply given by the momentum-space average of the time average (weighted by $\exp(\frac{t}{\tau})$) of $v_x(\mathbf{k}(t))$. We consider the case of $eB\tau \gg 1$. Then integration over t can be approximated by τ times the time average of $v_x(\mathbf{k}(t))$ over the trajectory of $\mathbf{k}(t)$. It might

be thought that σ_{xx} does not depend on the direction of the magnetic field, but it does, since the time-average is performed on the trajectory, which depends on the angle of the magnetic field. Since the speed of $\mathbf{k}(t)$ in the momentum space is proportional to $v_x(\mathbf{k}(t))$ when $|v_x| \gg |v_y|, |v_z|$, as seen from Eq. (4), time average of $v_x(\mathbf{k}(t))$ can be calculated as follows.

First, we consider the commensurate case, $\tan \theta = \frac{p}{q}$, where p and q are mutually prime integers. Brillouin zone is extended q times p as shown in Fig. 1(b). In the black region (area $S_1 = (2\pi)^2 w \delta^2$), $v_x = \alpha v_0$. The gray and black regions in Fig. 1(b) is defined as the set of $\mathbf{k}(0)$ that goes into the black region at some t . The area of the gray region is

$$\begin{aligned} S_0 &= (2\pi)^2 p \left(1 + \frac{w}{\tan \theta}\right) \delta - S_1 \\ &= (2\pi)^2 (p + qw - \delta w) \delta. \end{aligned} \quad (7)$$

We define $s_0 \equiv \frac{S_0}{(2\pi)^2} = (p + qw - \delta w) \delta$ and $s_1 \equiv \frac{S_1}{(2\pi)^2} = w \delta^2$. The gray region in Fig. 1(b) should be translated in the first Brillouin zone. Therefore, if $(p + qw) \delta > 1$, all the first Brillouin zone becomes black or gray region, i.e., every $\mathbf{k}(0)$ goes into S_1 . If $(p + qw) \delta < 1$, however, we can divide the first Brillouin zone into two regions, the first region ($S_1 + S_0$), and the second region $(2\pi)^2 - (S_1 + S_0)$. If $\mathbf{k}(0)$ is in the first region, $v_x(\mathbf{k}(t))$ changes the value as $\mathbf{k}(t)$ travels on the commensurate trajectory on the Fermi surface, while $v_x(\mathbf{k}(t))$ is time-independent constant v_0 for the $\mathbf{k}(0)$ in the second region. Now, we calculate the momentum-space average and time average of v_x , when the magnetic field is at the magic angle $\theta = \tan^{-1} \frac{p}{q}$ and $(p + qw) \delta < 1$. If $\mathbf{k}(0)$ is in S_1 or S_0 , the duration when $\mathbf{k}(t)$ is in the region S_1 is approximately proportional to $\frac{s_1}{\alpha v_0}$, while that in S_0 is approximately proportional to $\frac{s_0}{v_0}$. Thus the time average of $v_x(\mathbf{k}(t))$ when $\mathbf{k}(0)$ is in $S_1 + S_0$ is given by

$$\begin{aligned} \langle v_x \rangle^{(S_1+S_0)} &\approx \alpha v_0 \frac{\frac{s_1}{\alpha v_0}}{\frac{s_1}{\alpha v_0} + \frac{s_0}{v_0}} + v_0 \frac{\frac{s_0}{v_0}}{\frac{s_1}{\alpha v_0} + \frac{s_0}{v_0}} \\ &= v_0 \frac{s_1 + s_0}{\frac{s_1}{\alpha} + s_0} \end{aligned} \quad (8)$$

After the summation over $\mathbf{k}(0)$ in the Brillouin zone, we get the time and momentum-space average of v_x for the magic angle (commensurate orbit) as

$$\begin{aligned} \langle v_x \rangle^C &= v_0 (1 - s_1 - s_0) + \langle v_x \rangle^{(S_1+S_0)} (s_1 + s_0) \\ &= v_0 \left(1 + \frac{s_1(s_1 + s_0)(1 - \frac{1}{\alpha})}{\frac{s_1}{\alpha} + s_0} \right) \end{aligned} \quad (9)$$

Next, the time and momentum-space average of v_x is calculated for the case that $\tan \theta$ is irrational number or $(p + qw) \delta > 1$. In this case, $\mathbf{k}(t)$ goes into the region S_1 at some t regardless of the initial point $\mathbf{k}(0)$, i.e. the trajectory is incommensurate. The average of v_x is calculated




FIG. 2: Angular dependence of σ_{xx} for the model of k_y and k_z dependent v_x .




FIG. 3: Angular dependence of σ_{xx} for another choice of α , δ and w . In this case fewer peaks are seen but peak heights are large.

as

$$\begin{aligned} \langle v_x \rangle^{IC} &= \alpha v_0 \frac{\frac{s_1}{\alpha v_0}}{\frac{s_1}{\alpha v_0} + \frac{1-s_1}{v_0}} + v_0 \frac{\frac{1-s_1}{v_0}}{\frac{s_1}{\alpha v_0} + \frac{1-s_1}{v_0}} \\ &= v_0 \frac{1}{1 - s_1(1 - \frac{1}{\alpha})} \end{aligned} \quad (10)$$

From the above result we get the normalized peak heights of conductivity at the magic angles as

$$\begin{aligned} \frac{\sigma_{xx} - \sigma_{xx}^{IC}}{\sigma_{xx}^{IC}} &= \frac{\langle v_x \rangle^C - \langle v_x \rangle^{IC}}{\langle v_x \rangle^{IC}} \\ &= \frac{(1 - \alpha)^2 w^2 \delta^3}{\alpha} \frac{1 - (p + qw) \delta}{\alpha(p + qw) + w(1 - \alpha) \delta}, \end{aligned} \quad (11)$$

where the condition $(p + qw) \delta < 1$ should be satisfied.

In both cases of small velocity ($\alpha < 1$) and large velocity ($\alpha > 0$) in region S_1 , we get $\sigma_{xx} \geq \sigma_{xx}^{IC}$. The peak

heights becomes large ($\propto \frac{1}{\alpha}$) as α approaches to 0. In Figs. 2 and 3, we plot $(\sigma_{xx} - \sigma_{xx}^{IC})/\sigma_{xx}^{IC}$ for several parameters of α , δ and w . If s_1 is small, there are a lot of peaks at magic angles, $\tan^{-1} 1 = 45^\circ$, $\tan^{-1} 2 \approx 63.4^\circ$, $\tan^{-1} \frac{1}{2} \approx 26.6^\circ$, $\tan^{-1} \frac{1}{3} \approx 18.4^\circ$, etc. as seen in Fig. 2, but the heights of peaks are small. On the other hand, the number of peaks is small but their heights are large for larger s_1 (Fig. 3).

In conclusion we show that peaks in σ_{xx} at magic angles are large, when v_x depends on k_y and k_z on the Fermi surface of the quasi-one dimensional conductors. In the simple model that $v_x = v_0$ is constant except for in the rectangular region on the Fermi surface, where v_x is another constant value $v_x = \alpha v_0$, we get the approximate form of σ_{xx} by using the simple calculation of taking the momentum-space average on the Fermi surface and the time average on the trajectory of $\mathbf{k}(t)$. MAE is the consequence of the fact that $\mathbf{k}(t)$ stays shorter time in the region where $|v_x(k_y, k_z)|$ is large, and in the region of small $|v_x(k_y, k_z)|$, $\mathbf{k}(t)$ stays longer time. In this Letter, only σ_{xx} as a function of the tilting angle of the magnetic field is studied. The similar mechanism works also for σ_{zz} and the peak heights of σ_{zz} at the magic angles will be much more enhanced by considering the strong k_y and k_z dependence of v_x as done in this paper than that studied by Maki[21] and Lebed et al.[26, 27] in the perturbation theory in $\frac{t_b}{t_a}$. If we take account of the momentum-dependent relaxation time and more realistic momentum dependence of the velocity $v_x(k_y, k_z)$, experimentally observed peaks of σ_{xx} and σ_{zz} at magic angles will be explained better. Although MAE of σ_{xx} can be explained within the semiclassical theory, the strong momentum-dependence of the Fermi velocity, which may be caused by interactions between electrons, plays a crucial role to understand the magnitudes of the peak heights. This feature is in contrast to the other angle dependence of the conductivity in quasi-one and quasi-two dimensional conductors[15, 16, 17, 18] and usual quantum oscillations such as Shubnikov-de Haas oscillations, where the shape of the Fermi surface is important.

This work is partly supported by a Grant-in-Aid for the Promotion of Science and Scientific Research on Priority Areas (Grant No. 16038223) from the Ministry of Education, Culture, Sports, Science and Technology.

[1] T. Ishiguro, K. Yamaji, and G. Saito, Organic Superconductors, 2nd ed., (Springer-Verlag, Berlin, 1998).
[2] A. G. Lebed and P. Bak, Phys. Rev. Lett. **63**, 1315 (1989).
[3] T. Osada, A. Kawasumi, S. Kagoshima, N. Miura and G. Saito, Phys. Rev. Lett. **66**, 1525 (1991)
[4] M. J. Naughton, O. H. Chung, M. Chaparala, X. Bu and

P. Coppens, Phys. Rev. Lett. **67**, 3712 (1991).
[5] W. Kang, S. T. Hannahs and P. M. Chaikin, Phys. Rev. Lett. **69**, 2827 (1992).
[6] Chashechkina and P.M. Chaikin, Phys. Rev. Lett. **80**, 2181 (1998).
[7] W. Kang, H. Kang, Y.J. Jo and S. Uji, Synthetic Metals **133-134**, 15 (2003). H. Kang, Y.J. Jo, S. Uji and W. Kang, Phys. Rev. B **68**, 132508 (2003).
[8] S. Uji, C. Terakura, T. Terashima, H. Aoki, H. Nishikawa, I. Ikemoto and K. Kikuchi, Proceedings of Physical Phenomena at High Magnetic Fields-III, Ed. Z. Fisk, L. Gorkov and R. Schrieffer (World Scientific, 1998), p.277, Proceedings of the 4th International Symposium on Advanced Physical Fields (APF-4), Ed. G. Kido, p.295 (1999).
[9] H. Ito, D. Suzuki, Y. Yokochi, S. Kuroda, M. Umemiya, H. Miyasaka, K-I. Sugiura, M. Yamashita, and H. Tajima, Phys. Rev. B **71** 212503 (2005).
[10] N. Biškup, J.S. Brooks, R. Kato and K. Oshima, Phys. Rev. B **62**, 21 (2000).
[11] Y. Shimojo, M.A. Tanatar, T. Ishiguro and R. Kato, J. Phys. Soc. Jpn. **71**, 393 (2002).
[12] M.V. Kartsovnik, P.A. Kononovich, V.N. Laukhin and I.F. Shogole, Pis'ma Zh. Eksp. Theor. Fiz, **48**, 498 (1988), [JETP Lett. **48**,541 (1988)].
[13] K. Kajita, Y. Nishio, T. Takahashi, W. Sasaki, R. Kato, H. Kobayashi, A. Kobayashi, and Y. Iye, Solid state Commn. **70**, 1189 (1989).
[14] Y. Iye, R. Yagi, N. Hanasaki, S. Kagoshima, H. Mori, H. Fujimoto and G. Saito, J. Phys. Soc. Jpn. **63**, 674 (1994).
[15] G.M. Danner, W. Kang and P.M. Chaikin, Phys. Rev. Lett. **72**, 3714 (1994).
[16] T. Osada, S. Kagoshima and N. Miura, Phys. Rev. Lett. **77**, 5261 (1996).
[17] K. Yamaji, J. Phys. Soc. Jpn. **58**, 1520 (1989).
[18] R. Yagi, Y. Iye, T. Osada and S. Kagoshima, J. Phys. Soc. Jpn. **59**, 3069 (1990).
[19] T. Osada, S. Kagoshima and N. Miura, Phys. Rev. B **46**, 1812 (1992).
[20] P.M. Chaikin, Phys. Rev. Lett. **69**, 2831 (1992).
[21] K. Maki, Phys. Rev. B **45**, R5111 (1992).
[22] S.P. Strong, D.G. Clarke and P.W. Anderson, Phys. Rev. Lett. **73**, 1007 (1994).
[23] S.J. Blundell and J. Singleton, Phys. Rev. B **53**, 5609 (1996).
[24] P. Moses and R.H. McKenzie, Phys. Rev. B **63**, 024414 (2000).
[25] A. G. Lebed and M. J. Naughton, Phys. Rev. Lett. **91**, 187003 (2003).
[26] A. G. Lebed, N.N. Bagmet and M.J. Naughton, Phys. Rev. Lett. **93**, 157006 (2004).
[27] A.G. Lebed, H.I. Ha and M.J. Naughton, Phys. Rev. B **71**, 132504 (2005).
[28] U. Lundin and R.H. McKenzie, Phys. Rev. B **70**, 235122 (2004).
[29] W. Wu, P.M. Chaikin, W. Kang, J. Shinagawa, W. Yu and S.E. Brown, Phys. Rev. Lett. **94**, 097004 (2005)
[30] W. Wu, I.J. Lee and P.M. Chaikin, Phys. Rev. Lett. **91**, 056601 (2003).
[31] H. Kaneyasu, K. Kishigi and Y. Hasegawa, submitted to J. Phys. Soc. Jpn.